



ReCon FCE

High Strength Epoxy Fairing Coat and Blow Hole Filler

DESCRIPTION **ReCon FCE** is a two component solvent free epoxy system for rectifying irregularities on concrete surfaces.

USES **ReCon FCE** can be used for rectification of minor imperfections and pin holes in concrete surfaces, sealing of static cracks, general fair facing up to 3 mm thickness before application of resinous coatings, etc.

ADVANTAGES

- Easy to use
- Excellent bonding to the substrate
- No curing is required

TYPICAL PROPERTIES at 25°C

PROPERTY	TEST METHOD	VALUE
Component	-	Two: Part A- Base Part B- Hardener
Mixed Form	-	Paste
Colour	-	Off White or Grey
Potlife	-	70 +/-10 mins
Compressive Strength	BS 6319-2	70 N/mm ² at 7 days
Flexural Strength	BS 6319-3	20 N/mm ² at 7 days
Tensile Strength	BS 6319-7	15 N/mm ² at 7 days
Bond Strength	ASTM D4541	> 2 N/mm ² at 7 days
Application Temperature	-	+5°C to +40°C

SURFACE PREPARATION Concrete surfaces should be free from grease, oil, chemical contamination, dust, laitance and loose particles. It is preferred to use mechanical means like sand blasting or mechanical wire brushing. Steel surfaces should be grit blasted to white metal. Surfaces which show any traces of oil must be degreased with a chemical degreaser prior to grit blasting. Surfaces should be totally dry.

MIXING In order to produce a fully homogeneous paste, proper care should be taken to ensure that **ReCon FCE** is thoroughly mixed. The hardener and base components should be stirred thoroughly to disperse any settlement. The entire contents of the hardener should be emptied into the base container. Mix together using a mixing paddle attached to a slow speed (400 rpm) heavy duty drill, until a consistent uniform color paste is obtained. Under no circumstances should part packs be used or part mixing attempted.

APPLICATION Tools such as trowel, scraper, filling knife and squeegee can be used. Apply the mixed **ReCon FCE** to the prepared surface. Mixed material can be taken either directly from the can or subdivided onto spot boards. **ReCon FCE** can be over coated with epoxy coatings after a minimum curing period of 24 hours. Prior to over coating, the surface of the fully cured **ReCon FCE** should first be abraded to assist adhesion and then cleaned to a dust free finish.



ReCon FCE

PACK SIZE	1 ltr and 3 ltr set	
COVERAGE	2 m ² /ltr at 0.5 mm thickness	
LIMITATIONS	ReCon FCE should not be used in wet conditions. Due to exothermic reaction the mixed material will set in the container if not used within its pot life. Part mixing of material should be avoided.	
GENERAL INFORMATION	Shelf Life	12 months from date of manufacture when stored under warehouse conditions in original unopened packing. Extreme temperature / humidity may reduce shelf life.
	Cleaning	Clean all equipments and tools with Conmix Cleaner immediately after use. Hardened material can be removed mechanically.
HEALTH and SAFETY	PPE's	Gloves, goggles and suitable mask must be worn.
	Precautions	Contact with skin, eyes, etc. must be avoided. If swallowed seek medical attention immediately.
	Hazard	It is not readily flammable but combustible. It is regarded as non-hazardous for transportation.
	Disposal	Do not reuse containers. To be disposed off as per local rules and regulations.
	Additional Information	Refer MSDS. (Available on request.)
TECHNICAL SERVICE	CONMIX Technical Services are available on request for onsite support to assist in the correct use of its products.	

Manufacturer:
CONMIX LTD.
 P.O. Box 5936, Sharjah
 United Arab Emirates
 Tel: +971 6 5314155
 Fax: +971 6 5314332
 Email: conmix@conmix.com

Sales Office:
 Tel: +971 6 5682422
 Fax: +971 6 5681442
www.conmix.com



It is the customer's responsibility to satisfy themselves by checking with the company whether information is still current at the time of use. The customer must be satisfied that the product is suitable for the use intended. All products comply with the properties shown on current data sheets. However, Conmix does not warrant or guarantee the installation of the products as it does not have any control over installation or end use of the product. All information and particularly the recommendations relating to application and end use are given in good faith. The products are guaranteed against any manufacturing defects and are sold subject to Conmix standard terms and conditions of sale.